


SAVVI BRITE

Two Sided Coated GC1 Board which especially designed to answer the demand of premium graphical art and packaging applications by combining smoothness, glossiness and rigidity.



DOUBLE COATING	Min 30 gsm	Blade
TOP LAYER		NBKP + LBKP
UNDER LAYER		DIP
FILLER LAYER		BCTMP
BACK LAYER		LBKP
DOUBLE COATING	Min 30 gsm	Blade

GRAMMAGE T 410 om-02	THICKNESS ISO 534:1988 [E]		STIFFNESS TABER 15 ⁰ T 556 om-05			
	(g/m ²)	(µm)	(pt)	CD (gf.cm)	MD (gf.cm)	CD (mNm)
*] 210 ± 3%	225 ± 10	8.9 ± 0.4	34	62	3.3	6.0
*] 230 ± 3%	255 ± 10	10.0 ± 0.4	39	67	3.8	6.6
*] 240 ± 3%	280 ± 10	11.0 ± 0.4	44	75	4.3	7.4
260 ± 3%	305 ± 10	12.0 ± 0.4	54	90	5.1	8.0
290 ± 3%	355 ± 10	13.9 ± 0.4	84	132	8.2	12.9

Tolerance for Stiffness : ± 10%

PROPERTY

MOISTURE CONTENT T 412 om-02	%	6.0 ± 1.0
ROUGHNESS , pps (1.0 Mpa) T 555 om-04	210 - 240 260 - 290	Top µm Max 1.4 Top µm Max 1.6
BRIGHTNESS (D65/10 ⁰) ISO 2470	Top Back	% 93.0 ± 1.0 % 93.0 ± 1.0
GLOSS 75⁰ T 480 om-05	Top Back	% 60.0 ± 5.0 % 60.0 ± 5.0
INTERNAL BONDING SCOTT T 569 pm-00	J/m ²	Min 130
WATER ABSORPTION , COBB 60s T 441 om-04	Top Back	g/m ² 35 - 55 g/m ² 35 - 55

APPLICATIONS

High Quality Cover, Annual Report, Trading Cards, Advertising Brochures, and Packaging Application such as Cosmetics, Chocolates, Pharmaceuticals.

PRINTING METHOD

Offset, Letterpress

*) MOQ fulfillment

A good quality product by Serang Mill,



Does your paper have this?
Use APP paper and support responsible forest management.
Know what's in your paper and use resources wisely.
www.asiapulppaper.com

@AsiaPulpPaper @asiapulppaper



Rev. 02

Issued Date : September 16, 2020

All parameters measured to 95% confidence interval



Strategic Sales Channel - USA & Latin America

www.chartaglobal.com

Email: info@chartaglobal.com

Phone: +1 714-687-6648