


SinarBOARD-IG

Medium bulkiness white-back folding box board (GC1) which especially developed to serve for soap packaging applications by providing good appearance and strength properties to generate excellent quality and run-ability on both printing process.



DOUBLE COATING	Min 20 gsm	Blade
TOP LAYER		NBKP + LBKP
UNDER LAYER		BCTMP
FILLER LAYER		BCTMP
BACK LAYER		NBKP + LBKP
COATING	8 - 10 gsm	

Grammage (g/m ²) T 410 om - 02 (± 3%)	Stiffness Taber 15° T 489 om - 04				Caliper (pt) (± 0.4)	Thickness (µm) ISO 534 : 1988 (E) (± 10)
	CD (gf.cm)	MD (gf.cm)	CD (mNm)	MD (mNm)		
270	77	132	7.5	12.9	14.6	370
280	83	138	8.1	13.5	15.2	385
300	88	154	8.6	15.1	16.1	410

Tolerance for Stiffness : ± 10%

PROPERTY

Roughness

280 gsm Average Top 1.5 µm
Tolerance Top Max 2.0 µm

PPS (1.0 MPa) T 555 om - 99

Gloss 75°

T 480 om - 99

Brightness

ISO 2470

Moisture Content

T 412 om - 02

Internal Bond Strength

SCOTT T 569 pm - 00

Water Absorption

COBB₆₀

T 441 om - 98

Min 100 J/m²

Top 35-55 g/m²

APPLICATIONS

Soap Packaging

PRINTING METHOD

Offset, Letterpress.

*) Specialties : Fungi Resistance



SPECIFICATION FOR REFERENCE ONLY
Issued Date : November 02nd, 2015

FOR UPDATE and FURTHER INFORMATION

A good quality product by Serang Mill,



Does your paper have this?
Use APP paper and support responsible forest management.
Know what's in your paper and use resources wisely.
www.asiapulp.com

@Asi aPulpPaper asiapulp.com

CHARTA GLOBAL

Strategic Sales Channel - USA & Latin America
www.chartaglobal.com
Email: info@chartaglobal.com
Phone: +1 714-687-6648